

**GUR® 4056-3**

(PE-UHMW)

Celanese

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Shore D hardness	<b>60</b>	-	ISO 7619-1

[C]: CAMPUS

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>38</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	<b>80</b>	°C	ISO 306

[C]: CAMPUS

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	<b>1E12</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>1E12</b>	Ohm	IEC 62631-3-2

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>930</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Delivery form**

Powder