

Polimaxx U320FW
(PE-UHMW)

IRPC

| Thermal properties | Value | Unit | Test Standard |
|--------------------------------|--------------|-------------------|----------------------|
| ISO Data | | | |
| Vicat softening temperature, A | 128 | °C | ISO 306 |
| ASTM Data | | | |
| Melting Temperature | 132 | °C | ASTM D 3418 |
| Other properties | | | |
| Density | 930 | kg/m ³ | ISO 1183 |
| Intrinsic Viscosity | 17.5 | dl/g | - |
| Bulk density | 400 | kg/m ³ | - |

Characteristics

Delivery form

Powder

Regional Availability

Europe, Asia Pacific

Certifications

RoHS compliant