

RTP 2099 X 126210 BLACK

(PLA+PC)

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	51.7	MPa	ASTM D 638
Flexural Modulus	2551	MPa	ASTM D 790
Flexural Strength	86.2	MPa	ASTM D 790
Izod Impact notched, 1/8 in	694	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 66 psi	124	°C	ASTM D 648
DTUL @ 264 psi	68.3	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Biobased content	32	%	-
Density	1200	kg/m ³	ASTM D 792
Moisture Content	0.02	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	79.4	°C	-
Pre-drying - Time	4	h	-
Melt temperature	221 - 243	°C	-
Mold temperature	23.9 - 71.1	°C	-
Injection pressure	55.2 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Certifications

Contains renewable resources

Delivery form

Black

Regional Availability

North America, Europe, Asia Pacific