

Denilub M 00U 22TFAr
(POM+PTFE)-AF

VAMP TECH SPA

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Izod impact strength, +23°C	25	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	5	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	4000	MPa	ASTM D 638
Tensile Strength at Yield	60	MPa	ASTM D 638
Elongation at Break	7	%	ASTM D 638
Thermal properties			
ASTM Data			
DTUL @ 264 psi	110	°C	ASTM D 648
Vicat Temperature	150	°C	ASTM D 1525
Other properties			
Density	1440	kg/m ³	ASTM D 792

Characteristics

Additives

Lubricants

Regional Availability

Europe

Special Characteristics

Flame retardant