

**Product Texts**

LNP LUBRICOMP KAL22XXC compound is based on Acetal (POM) Copolymer resin containing 10% PTFE, 10% aramid fiber. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E45329-101344678](https://www.ulprospector.com/usa/Products/Plastics/101344678)

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>2700</b>	MPa	ISO 527
Yield stress	<b>50</b>	MPa	ISO 527
Yield strain	<b>11</b>	%	ISO 527
Stress at break	<b>50</b>	MPa	ISO 527
Strain at break	<b>11</b>	%	ISO 527
Flexural modulus	<b>2700</b>	MPa	ISO 178
Izod impact strength, +23°C, 4mm	<b>45</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	<b>7</b>	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>80</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>102</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	<b>125</b>	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1450</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>4</b>	h	-
Melt temperature	<b>200 - 215</b>	°C	-
Mold temperature	<b>80 - 110</b>	°C	-
Zone 1	<b>175 - 190</b>	°C	-
Zone 2	<b>195 - 205</b>	°C	-
Zone 3	<b>210 - 220</b>	°C	-
Screw speed	<b>30 - 60</b>	rpm	-
Back pressure	<b>0.2 - 0.3</b>	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Regional Availability**

Europe