

**Product Texts**

LNP LUBRICOMP KX06415 compound is based on Acetal (POM) Copolymer resin containing 10% PTFE, 10% aramid powder. Added features of this grade include: Easy Molding, Heat Stabilized, Wear Resistant.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	3	mm/mm	ASTM D 955
Mold Shrinkage, TD	3	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2590	MPa	ISO 527
Yield strain	8.8	%	ISO 527
Stress at break	39	MPa	ISO 527
Strain at break	14	%	ISO 527
Flexural modulus	2420	MPa	ISO 178
Flexural strength	62	MPa	ISO 178
Izod impact strength, +23°C, 4mm	26	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	5	kJ/m <sup>2</sup>	ISO 180/1A

ASTM Data	Value	Unit	Test Standard
Tensile Modulus	2860	MPa	ASTM D 638
Tensile Strength at Break	41	MPa	ASTM D 638
Elongation at Yield	8.5	%	ASTM D 638
Elongation at Break	14	%	ASTM D 638
Flexural Modulus	2430	MPa	ASTM D 790
Izod Impact notched, 1/8 in	36	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	367	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	84	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	147	°C	ISO 75-1/-2
<b>ASTM Data</b>			
Coefficient of Thermal Expansion, MD	99	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	104	E-6/K	ASTM D 696
DTUL @ 66 psi	155	°C	ASTM D 648
DTUL @ 264 psi	94	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Humidity absorption	0.35	%	Sim. to ISO 62
Water Absorption, 24hr	0.21	%	ASTM D 570
Density	1400	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	200 - 215	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	175 - 190	°C	-
Zone 2	195 - 205	°C	-
Zone 3	210 - 220	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific