

Witcom POM-C/2A/2L1

(POM+PTFE)-AF10

Wittenburg B.V.

Product Texts

10% PTFE

Processing/Physical Characteristics**ISO Data**

	Value	Unit	Test Standard
Molding shrinkage, parallel	1.8	%	ISO 294-4, 2577

Mechanical properties**ISO Data**

	Value	Unit	Test Standard
Tensile Strength	55	MPa	ISO 527
Strain at break	5	%	ISO 527
Flexural modulus, 23°C	3200	MPa	ISO 178
Flexural strength	70	MPa	ISO 178
Izod impact strength, +23°C	50	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	8	kJ/m ²	ISO 180/1A

Thermal properties**ISO Data**

	Value	Unit	Test Standard
Temp. of deflection under load, 1.80 MPa	130	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	80	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Electrical properties**ISO Data**

	Value	Unit	Test Standard
Comparative tracking index	600	-	IEC 60112

ASTM Data

Surface Resistivity	1E14	Ohm	ASTM D 257
Volume Resistivity	1E15	Ohm*cm	ASTM D 257

Other properties

	Value	Unit	Test Standard
Water absorption	1.2	%	Sim. to ISO 62
Humidity absorption	0.3	%	Sim. to ISO 62
Density	1450	kg/m ³	ISO 1183

Characteristics**Additives**

Lubricants

Regional Availability

Europe

Features

Copolymer