

**LubriOne™ AT-10CF/5T BLACK**  
(POM+PTFE)-CF10

Avient Corporation

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.0105</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>55</b>	MPa	ASTM D 638
Flexural Modulus	<b>7500</b>	MPa	ASTM D 790
Flexural Strength	<b>102</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>50</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>1.6</b>	mm	-
DTUL @ 264 psi	<b>140</b>	°C	ASTM D 648

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Surface Resistivity	<b>1000000</b>	Ohm	ASTM D 257

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1440</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>80 - 90</b>	°C	-
Pre-drying - Time	<b>2 - 3</b>	h	-
Mold temperature	<b>75 - 85</b>	°C	-
Zone 1	<b>190 - 200</b>	°C	-
Zone 2	<b>190 - 200</b>	°C	-
Zone 3	<b>190 - 200</b>	°C	-

**Characteristics**

**Processing**  
Injection Molding

**Features**  
Copolymer

**Delivery form**  
Black

**Regional Availability**  
Asia Pacific

**Additives**  
Lubricants