

RTP 803 CC TFE 15
(POM+PTFE)-GF20

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	7584	MPa	ASTM D 638
Tensile Strength	89.6	MPa	ASTM D 638
Flexural Modulus	6895	MPa	ASTM D 790
Flexural Strength	138	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	157	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1650	kg/m ³	ASTM D 792
Moisture Content	0.15	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	2	h	-
Melt temperature	182 - 218	°C	-
Mold temperature	79.4 - 107	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics

Processing

Injection Molding

Additives

Lubricants

Regional Availability

North America, Europe, Asia Pacific