

Product Texts

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

Delrin® 520MP is a medium viscosity acetal homopolymer containing 20% PTFE Micropowder lubricant. It is designed for applications requiring low wear and friction against steel, itself, or other plastics.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.9	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.5	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	4	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	1.05	kg	-
Mold Shrinkage, MD	0.0195	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0155	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2900	MPa	ISO 527
^[C] Yield stress	53	MPa	ISO 527
^[C] Yield strain	13	%	ISO 527
^[C] Nominal strain at break	10	%	ISO 527
^[C] Tensile creep modulus, 1h	1500	MPa	ISO 899-1
^[C] Tensile creep modulus, 1000h	800	MPa	ISO 899-1
^[C] Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	3	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	4	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Modulus	3130	MPa	ASTM D 638
Tensile Strength	54	MPa	ASTM D 638
Tensile Strength at Yield	54	MPa	ASTM D 638
Elongation at Yield	12	%	ASTM D 638
Elongation at Break	14	%	ASTM D 638
Flexural Modulus	3100	MPa	ASTM D 790
Izod Impact notched, 1/8 in	32	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	178	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	94	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	160	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	100	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	100	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	166	°C	ASTM D 648

Delrin® 520MP NC010
(POM+PTFE)-Z20

Delrin

DTUL @ 264 psi	102	°C	ASTM D 648
Melting Temperature	178	°C	ASTM D 3418

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	90	E-4	IEC 62631-2-1
ASTM Data			
Dielectric Strength, Short Time	18	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.005	-	ASTM D 150
Dielectric Constant, 1 MHz	3.4	-	ASTM D 150
Surface Resistivity	>1E15	Ohm	ASTM D 257
Volume Resistivity	3E14	Ohm*cm	ASTM D 257

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1540	kg/m ³	ISO 1183
Density	1540	kg/m ³	ASTM D 792

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Film Extrusion, Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion, Wire/Cable Extrusion, Other Extrusion

Delivery form

Pellets, Natural Color

Additives

Lubricants, Release agent

Features

Tribologic Grade, Weldable, Homopolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Injection molding

Drying is recommended, but not necessary for newly opened packaging stored in a dry location.

Follow the drying guidelines above in the following cases:

- If moisture is above the Processing Moisture Content recommendation,
- When a resin container is damaged,
- When the material is not properly stored in a dry place at room temperature, or
- When packaging stays open for a significant time.