

**Denilub M 00U 40TFSi**

(POM+PTFE+SI)

VAMP TECH SPA

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Izod impact strength, +23°C	<b>20</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	<b>3</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Modulus	<b>1500</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>35</b>	MPa	ASTM D 638
Elongation at Break	<b>10</b>	%	ASTM D 638
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>85</b>	°C	ASTM D 648
Vicat Temperature	<b>142</b>	°C	ASTM D 1525
<b>Other properties</b>			
Density	<b>1500</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Additives**

Lubricants

**Regional Availability**

Europe

**Special Characteristics**

Flame retardant