

4POM 23I15200

(POM+SI)

4Plas

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2900	MPa	ISO 527
Stress at break	66	MPa	ISO 527
Strain at break	25	%	ISO 527
Izod notched impact strength, +23°C	7	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	166	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	156	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Other properties	Value	Unit	Test Standard
Density	1410	kg/m ³	ISO 1183

Characteristics**Additives**

Lubricants

Regional Availability

Europe