

Denilub M 00U 0Si

(POM+SI)

VAMP TECH SPA

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	6.5	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	2000	MPa	ASTM D 638
Tensile Strength at Yield	50	MPa	ASTM D 638
Elongation at Break	100	%	ASTM D 638
Thermal properties			
ASTM Data			
DTUL @ 264 psi	85	°C	ASTM D 648
Vicat Temperature	145	°C	ASTM D 1525
Other properties			
Density	1390	kg/m ³	ASTM D 792

Characteristics**Additives**

Lubricants

Regional Availability

Europe

Special Characteristics

Flame retardant