

Polywood PET 30 PP 48 A1

(PP+PET)

Grade is obsolete.

Advanced Compounding GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1500	MPa	ISO 527
Tensile Strength	20	MPa	ISO 527
Strain at break	19.5	%	ISO 527
Charpy impact strength, +23°C	35	kJ/m ²	ISO 179/1eU

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Certifications

Contains renewable resources

Applications

Automotive

Regional Availability

Europe