

Badamid® PPA-HP CF30 H

(PPA+PA66)-CF30

Bada AG

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	25000 / 23000	MPa	ISO 527
Stress at break	280 / 250	MPa	ISO 527
Strain at break	1.6 / 1.8	%	ISO 527
Charpy impact strength, +23°C	50 / 60	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	14 / -	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	270 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Volume resistivity	1000 / -	Ohm*m	IEC 62631-3-1

Other properties	dry / cond	Unit	Test Standard
Water absorption	4 / *	%	Sim. to ISO 62
Humidity absorption	1 / *	%	Sim. to ISO 62
Density	1300 / -	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	290 - 320	°C	-
Mold temperature	135	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa