

Denilub Z 30G 3TF

(PPA+PTFE)-GF30

VAMP TECH SPA

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Izod impact strength, +23°C	45	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	7	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	12000	MPa	ASTM D 638
Tensile Strength at Yield	175	MPa	ASTM D 638
Elongation at Break	2	%	ASTM D 638
Thermal properties			
ASTM Data			
DTUL @ 264 psi	280	°C	ASTM D 648
Other properties			
Density	1540	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	90	°C	-
Pre-drying - Time	3	h	-
Melt temperature	315	°C	-
Mold temperature	120	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant

Additives

Lubricants

Regional Availability

Europe