

NORYL GTX™ Resin GTX6011 - Asia

(PPE+PA*)

Saudi Basic Industries Corporation (SABIC)

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	1860	MPa	ASTM D 790
Flexural Strength	74	MPa	ASTM D 790
Izod Impact notched, 1/8 in	843	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	180	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1070	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific

Applications

Automotive