

NORYL GTX™ Resin GTX4610 - Asia

(PPE+PA*)-GF10

Saudi Basic Industries Corporation (SABIC)

Product Texts

NORYL GTX™ 4610 resin is a 10% glass reinforced alloy of Polyphenylene Ether (PPE) + Polyamide (PA). This high performance injection moldable grade has a UL 5VA flame rating, non-brominated / non-chlorinated FR package, UL746C Outdoor Suitability rating of F1, excellent chemical resistance, high heat resistance, high flow, and is laser weldable. NORYL GTX4610 resin is an excellent candidate for a wide variety of electrical applications including connectors, sockets, sensors, terminal blocks and insulator components. NORYL GTX™ 4610 resin is also an excellent candidate for electric vehicle (EV) battery applications including housings and covers.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	15	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	5	kg	-
ASTM Data			
Melt Flow Index, MFI	18	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	5	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	5000	MPa	ISO 527
Yield stress	88	MPa	ISO 527
Yield strain	3	%	ISO 527
Stress at break	88	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus	4600	MPa	ISO 178
Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C, 4mm	5	kJ/m ²	ISO 180/1A
Izod notched impact strength, -30°C, 4mm	5	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	5000	MPa	ASTM D 638
Tensile Strength at Yield	88	MPa	ASTM D 638
Tensile Strength at Break	88	MPa	ASTM D 638
Elongation at Yield	3	%	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	4600	MPa	ASTM D 790
Izod Impact notched, 1/8 in	80	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	65	J/m	ASTM D 256
Temperature	-30	°C	-

Thermal properties

	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	224	°C	ISO 75-1/-2
Vicat softening temperature, B	218	°C	ISO 306
Vicat softening temperature, 120°C/h 50N	220	°C	ISO 306
ASTM Data			
DTUL @ 66 psi	220	°C	ASTM D 648
Vicat Temperature	218	°C	ASTM D 1525

Electrical properties

	Value	Unit	Test Standard
ISO Data			
Comparative tracking index	425	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	24.4	kV/mm	ASTM D 149
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257

Other properties

	Value	Unit	Test Standard
Water absorption	3.8	%	Sim. to ISO 62
Humidity absorption	0.5	%	Sim. to ISO 62
Density	1210	kg/m ³	ISO 1183

Density	1210	kg/m ³	ASTM D 792
---------	-------------	-------------------	------------

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	95 - 105	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.07	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	75 - 120	°C	-
Zone 1	265 - 305	°C	-
Zone 2	270 - 305	°C	-
Zone 3	275 - 305	°C	-
Screw speed	20 - 100	rpm	-
Back pressure	0.3 - 1.4	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

Asia Pacific

Applications

Automotive