

NORYL GTX™ Resin GTX830 - Americas

(PPE+PA*)-GF30

Saudi Basic Industries Corporation (SABIC)

Product Texts

NORYL GTX™ 830 resin is a 30% glass reinforced alloy of Polyphenylene Ether (PPE) + Polyamide (PA). This injection moldable grade has high stiffness (flexural modulus 8200 MPa), excellent chemical resistance, and high heat resistance. NORYL GTX GTX830 resin is an excellent candidate for a wide variety of applications including automotive under the bonnet applications and water meter housings.

UL Yellow Card Link [E121562-220762](https://www.ul.com/yellow-card/E121562-220762)

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	106	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	80	J/m	ASTM D 256
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
ASTM Data			
Vicat Temperature	248	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.5	%	ASTM D 570
Density	1330	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	95 - 105	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.07	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	75 - 120	°C	-
Zone 1	265 - 305	°C	-
Zone 2	270 - 305	°C	-
Zone 3	275 - 305	°C	-
Screw speed	20 - 100	rpm	-
Back pressure	0.3 - 1.4	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America

Applications

Automotive