

NORYL GTX™ Resin GTX6801 - Asia

(PPE+PA*)-GF30

Saudi Basic Industries Corporation (SABIC)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	24.2	g/10min	ASTM D 1238
Temperature	280	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	8430	MPa	ASTM D 790
Flexural Strength	216	MPa	ASTM D 790
Izod Impact notched, 1/8 in	88	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1330	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific

Applications

Automotive