

NORYL PPX™ Resin PPX630 - Asia

(PPE+PP)-GF30

Saudi Basic Industries Corporation (SABIC)

Product Texts

NORYL PPX™ 630 resin is a 30% glass reinforced alloy of polyphenylene ether (PPE) + polypropylene (PP). This injection moldable grade exhibits high elongation and high stiffness along with temperature performance, impact resistance, hydrolytic and dimensional stability. NORYL PPX630 resin is an excellent candidate for hot water system exteriors, condensate housings, and printer internals.

*See NORYL PPX630F resin for NSF 61.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2.6	g/10min	ASTM D 1238
Temperature	260	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	79	MPa	ASTM D 638
Tensile Strength at Break	79	MPa	ASTM D 638
Elongation at Break	7.7	%	ASTM D 638
Flexural Modulus	5550	MPa	ASTM D 790
Izod Impact notched, 1/8 in	165	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	101	J/m	ASTM D 256
Temperature	-30	°C	-
Izod Impact unnotched, 1/8 in	827	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	155	°C	ASTM D 648
DTUL @ 264 psi	133	°C	ASTM D 648
Vicat Temperature	162	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	65 - 75	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	260 - 300	°C	-
Mold temperature	40 - 65	°C	-
Zone 1	245 - 290	°C	-
Zone 2	250 - 290	°C	-
Zone 3	255 - 295	°C	-
Screw speed	20 - 100	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

Asia Pacific