

Product Texts

NORYL™ FE1520PW resin is a 20% glass reinforced blend of polyphenylene ether (PPE) + crystal clear polystyrene (ccPS). This injection moldable material is FC EU, FDA food contact compliant, NSF/ANSI 61*, ACS, WRAS, KTW, and W270 listed for global potable water use. NORYL FE1520PW resin exhibits excellent long-term hydrolytic stability, very low moisture absorption, heat / hot water resistance and is an excellent candidate for a variety of water management applications such as pump housings, impellers, shower/faucet, membrane housings and valves. *NSF certification is color dependent.

UL Yellow Card Link [E45329-101519378](https://www.ulprospector.com/usa/Products/Plastics/Engineering-Plastics/101519378)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	22	cm ³ /10min	ISO 1133
Temperature	280	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7170	MPa	ISO 527
Stress at break	119	MPa	ISO 527
Strain at break	2.6	%	ISO 527
Flexural modulus	6040	MPa	ISO 178
Charpy impact strength, +23°C	30	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, -30°C	5	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C, 4mm	25	kJ/m ²	ISO 180/1U
Izod impact strength, -30°C, 4mm	23	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	6	kJ/m ²	ISO 180/1A
Izod notched impact strength, -30°C, 4mm	4	kJ/m ²	ISO 180/1A
Ball indentation hardness	220	MPa	ISO 2039-1

ASTM Data			
Tensile Modulus	7100	MPa	ASTM D 638
Tensile Strength at Break	119	MPa	ASTM D 638
Elongation at Break	2.6	%	ASTM D 638
Flexural Modulus	6970	MPa	ASTM D 790
Izod Impact notched, 1/8 in	65	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	45	J/m	ASTM D 256
Temperature	-30	°C	-
Izod Impact unnotched, 1/8 in	400	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, A	150	°C	ISO 306
Vicat softening temperature, 120°C/h 50N	144	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

ASTM Data			
DTUL @ 264 psi	135	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Water absorption	0.2	%	Sim. to ISO 62
Density	1240	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 120	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	290 - 320	°C	-
Mold temperature	80 - 120	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	270 - 280	°C	-

NORYL™ Resin FE1520PW - Europe

(PPE+PS)-GF20

Saudi Basic Industries Corporation (SABIC)

Zone 2	280 - 300	°C	-
Zone 3	300 - 310	°C	-

Characteristics**Processing**

Injection Molding

Certifications

Food contact, Food approval FDA 21 CFR

Chemical Resistance

Hydrolytically Stable

Regional Availability

Europe