

NORYL™ Resin FM3020V - Asia

(PPE+PS)-X30

Saudi Basic Industries Corporation (SABIC)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	19.2	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Flexural Modulus	6370	MPa	ASTM D 790
Flexural Strength	113	MPa	ASTM D 790

Other properties	Value	Unit	Test Standard
Density	1090	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

Asia Pacific