

Deloxen P 3010

(PPO+PP)-GF30

VAMP TECH SPA

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Izod impact strength, +23°C	30	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	13	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	6000	MPa	ASTM D 638
Tensile Strength at Yield	70	MPa	ASTM D 638
Elongation at Break	2.5	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	145	°C	ASTM D 648
Vicat Temperature	140	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	3	h	-
Melt temperature	280	°C	-
Mold temperature	80	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe