

RTP 1385 TFE 15
(PPS+PTFE)-CF30

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.00075	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	24130	MPa	ASTM D 638
Tensile Strength	162	MPa	ASTM D 638
Flexural Modulus	22750	MPa	ASTM D 790
Flexural Strength	241	MPa	ASTM D 790
Izod Impact notched, 1/8 in	53.4	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	266	°C	ASTM D 648
Electrical properties			
ASTM Data			
Surface Resistivity	1000	Ohm	ASTM D 257
Volume Resistivity	10	Ohm*cm	ASTM D 257
Other properties			
Water Absorption, 24hr	0.02	%	ASTM D 570
Density	1540	kg/m ³	ASTM D 792
Moisture Content	0.04	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	6	h	-
Melt temperature	307 - 329	°C	-
Mold temperature	135 - 177	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Additives

Lubricants