

**Witcom PPS/6C/3L1-L**

(PPS+PTFE)-CF30

Wittenburg B.V.

**Product Texts**

15% PTFE

**Processing/Physical Characteristics****ISO Data**

	Value	Unit	Test Standard
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577

**Mechanical properties****ISO Data**

	Value	Unit	Test Standard
Tensile Strength	185	MPa	ISO 527
Strain at break	1	%	ISO 527
Flexural modulus, 23°C	22000	MPa	ISO 178
Flexural strength	260	MPa	ISO 178
Izod impact strength, +23°C	30	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	6	kJ/m <sup>2</sup>	ISO 180/1A

**Thermal properties****ISO Data**

	Value	Unit	Test Standard
Temp. of deflection under load, 1.80 MPa	260	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	22	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1.6	mm	-
Glow Wire Ignition Temperature (GWIT)	960	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1.6	mm	-

**Electrical properties****ASTM Data**

	Value	Unit	Test Standard
Surface Resistivity	1000	Ohm	ASTM D 257
Volume Resistivity	1000	Ohm*cm	ASTM D 257

**Other properties**

	Value	Unit	Test Standard
Water absorption	0.05	%	Sim. to ISO 62
Humidity absorption	0.03	%	Sim. to ISO 62
Density	1520	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Additives**

Lubricants

**Regional Availability**

Europe

**Special Characteristics**

Increased electrical conductivity