

Product Texts

Base Polymer	Polyphenylene Sulphide
Filler/Additive System	40 % glass fibres,10 % PTFE
Special Features	improved sliding / wear,high stiffness,high toughness
Market Segment	Automotive,Machinery
Typical Applications	bearings and sliding elements,functional components

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	15700	MPa	ISO 527
^[C] Stress at break	180	MPa	ISO 527
^[C] Strain at break	1.7	%	ISO 527
^[C] Charpy impact strength, +23°C	45	kJ/m ²	ISO 179/1eU

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	275	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1730	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Other text information

Injection molding

Pre-Drying Conditions	in a dry air (dessiccant) dryer 130-140 °C for 2-4 h dependant on moisture content
Processing Injection Moulding	melt temperature 320-340 °C mould temperature >140 °C
Storage	dry, protected from light not above 30°C