

LATILUB 80-17ST G/30

(PPS+PTFE+SI)-GF

LATI Industria Termoplastici S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	11000	MPa	ISO 527
Stress at break	135	MPa	ISO 527
Strain at break	1.7	%	ISO 527
Charpy impact strength, +23°C	25	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	265	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	275	°C	ISO 75-1/-2
Vicat softening temperature, B	255	°C	ISO 306

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1670	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	130 - 150	°C	-
Pre-drying - Time	3	h	-
Melt temperature	290 - 310	°C	-
Mold temperature	130 - 150	°C	-

Characteristics**Processing**

Injection Molding

Additives

Lubricants

CertificationsFood contact, Drinking water contact, Drinking water contact
NSF 61**Regional Availability**

Europe