

Vamplub F 40G 00TFSi

(PPS+PTFE+SI)-GF40

VAMP TECH SPA

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Izod impact strength, +23°C	32	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	5	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	14000	MPa	ASTM D 638
Tensile Strength at Yield	150	MPa	ASTM D 638
Elongation at Break	1.6	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
ASTM Data			
DTUL @ 264 psi	265	°C	ASTM D 648
Vicat Temperature	255	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1670	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	130	°C	-
Pre-drying - Time	3	h	-
Melt temperature	320	°C	-
Mold temperature	140	°C	-

Characteristics**Processing**

Injection Molding

Additives

Lubricants

Special Characteristics

Flame retardant

Certifications

RoHS compliant

Regional Availability

Europe