

LNP™ LUBRICOMP™ Compound GL003 - Americas

(PSU+PTFE)

Saudi Basic Industries Corporation (SABIC)

Product Texts

LNP LUBRICOMP GL003 compound is based on Polysulfone (PSU) resin containing 15% PTFE. Added features of this grade include: Wear Resistant.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.8	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.8	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	55	MPa	ISO 527
Strain at break	11.8	%	ISO 527
Flexural modulus	2300	MPa	ISO 178
Flexural strength	78	MPa	ISO 178
Izod impact strength, +23°C, 4mm	70	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	6	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Strength at Break	55	MPa	ASTM D 638
Elongation at Break	9.9	%	ASTM D 638
Flexural Modulus	2060	MPa	ASTM D 790
Flexural Strength	75	MPa	ASTM D 790
Izod Impact notched, 1/8 in	58	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	891	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	175	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	179	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	178	°C	ASTM D 648
DTUL @ 264 psi	170	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1310	kg/m ³	ISO 1183
Water Absorption, 24hr	0.1	%	ASTM D 570
Density	1310	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	360 - 370	°C	-
Mold temperature	150	°C	-
Zone 1	325 - 340	°C	-
Zone 2	340 - 350	°C	-
Zone 3	350 - 360	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America