

Product Texts

LNP LUBRICOMP GFL36 compound is based on Polysulfone (PSU) resin containing 30% glass fiber and 15% PTFE. Added features of this grade include: Internally Lubricated, Wear Resistant.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	8900	MPa	ISO 527
Stress at break	92	MPa	ISO 527
Strain at break	1.6	%	ISO 527
Flexural modulus	7400	MPa	ISO 178
Izod impact strength, +23°C, 4mm	25	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	8	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	185	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	17	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	44	E-6/K	ISO 11359-1/-2

Other properties	Value	Unit	Test Standard
Density	1580	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 150	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	360 - 370	°C	-
Mold temperature	150	°C	-
Zone 1	325 - 340	°C	-
Zone 2	340 - 350	°C	-
Zone 3	350 - 360	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific