

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	15.2	MPa	ASTM D 638
Elongation at Break	380	%	ASTM D 638
Shore A Hardness	81	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1320	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	193 - 204	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Chemical Resistance

Oil Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa