

Geon™ Vinyl Flexible R263AM
(PVC+NBR)

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	13.1	MPa	ASTM D 638
Elongation at Break	380	%	ASTM D 638
Shore A Hardness	61	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	185 - 196	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa