

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	8.27	MPa	ASTM D 638
Elongation at Break	450	%	ASTM D 638
Shore A Hardness	51	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ASTM D 792

Characteristics

Processing

Blow Molding

Delivery form

Pellets

Chemical Resistance

Oil Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa