

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	16.7	MPa	ASTM D 638
Elongation at Break	400	%	ASTM D 638
Shore A Hardness	70	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1270	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	188 - 199	°C	-

Characteristics

Processing

Injection Molding, Pipe/Tube Extrusion, Profile Extrusion, Other Extrusion

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa