

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2620	MPa	ASTM D 638
Tensile Strength at Yield	52.9	MPa	ASTM D 638
Flexural Modulus	2730	MPa	ASTM D 790
Flexural Strength	94.5	MPa	ASTM D 790
Shore D Hardness	84	-	ASTM D 2240
Izod Impact notched, 1/8 in	130	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	89.9	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1520	kg/m ³	ASTM D 792

Characteristics

Processing

Profile Extrusion, Other Extrusion

Delivery form

Pellets

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa