

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2990	MPa	ASTM D 638
Tensile Strength at Yield	55.2	MPa	ASTM D 638
Flexural Modulus	3380	MPa	ASTM D 790
Rockwell Hardness	R 117	-	ASTM D 785
Izod Impact notched, 1/8 in	96	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1500	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	198 - 210	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa