

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2520	MPa	ASTM D 638
Tensile Strength at Yield	49.6	MPa	ASTM D 638
Shore D Hardness	76	-	ASTM D 2240
Izod Impact notched, 1/8 in	160	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1530	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa