

ProTherm® 4353

(PVC-C)

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2937	MPa	ASTM D 638
Tensile Strength	54.5	MPa	ASTM D 638
Tensile Strength at Yield	54.5	MPa	ASTM D 638
Izod Impact notched, 1/8 in	155	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	113	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1500	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Chemical Resistance

General Chemical Resistance

Delivery form

Powder

Regional Availability

North America