

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	<b>1.2</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>1.3</b>	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Stress at 10% elongation	<b>1.3</b>	MPa	ISO 527
Stress at 100% elongation	<b>3.4</b>	MPa	ISO 527
Stress at 300% elongation	<b>4.9</b>	MPa	ISO 527
Stress at break TPE	<b>7.5</b>	MPa	ISO 527
Strain at break TPE	<b>650</b>	%	ISO 527
Shore D hardness	<b>25</b>	-	ISO 7619-1

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1010</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Certifications**

Food contact, Food approval 10/2011

**Regional Availability**

Europe

**Applications**

Automotive, Medical, Packaging, Sports Equipment