

**RTP 2505 A TFE 15**

(TPU+PTFE)-GF30

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.001</b>	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	<b>7929</b>	MPa	ASTM D 638
Tensile Strength	<b>121</b>	MPa	ASTM D 638
Flexural Modulus	<b>7929</b>	MPa	ASTM D 790
Flexural Strength	<b>179</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>149</b>	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	<b>1550</b>	kg/m <sup>3</sup>	ASTM D 792
Moisture Content	<b>0.01</b>	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>107</b>	°C	-
Pre-drying - Time	<b>4 - 6</b>	h	-
Melt temperature	<b>221 - 243</b>	°C	-
Mold temperature	<b>51.7 - 93.3</b>	°C	-
Injection pressure	<b>68.9 - 103</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific

**Additives**

Lubricants