

**Nemcon™ E ABS 20CF**

ABS-CF20

Ovation Polymers

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>10500</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>95</b>	MPa	ASTM D 638
Elongation at Break	<b>1.9</b>	%	ASTM D 638
Flexural Modulus	<b>9535</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>45.9</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>98</b>	°C	ASTM D 648
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Surface Resistivity	<b>2750</b>	Ohm	ASTM D 257
<b>Other properties</b>			
Density	<b>1130</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Increased electrical conductivity

**Applications**

Electrical and Electronical

**Regional Availability**

North America