

POLYabs S00 GK10

ABS-GF10

Polykemi AB

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Strength	34	MPa	ISO 527
Yield strain	6	%	ISO 527
Flexural modulus, 23°C	2300	MPa	ISO 178
Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	78	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	92	°C	ISO 75-1/-2
Vicat softening temperature, A	106	°C	ISO 306
Vicat softening temperature, B	100	°C	ISO 306
Other properties			
Density	1110	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific

Delivery form

Granules