

CILAC FV 17 T

ABS-GF17

MAIP SRL

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	4	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.3	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	5000	MPa	ISO 527
Yield stress	65	MPa	ISO 527
Stress at break	65	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus, 23°C	5200	MPa	ISO 178
Flexural strength	100	MPa	ISO 178
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	7	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Glass transition temperature, 10°C/min	100	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	105	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	45	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	50	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Burning rate, FMVSS, Thickness 1 mm	45	mm/min	ISO 3795 (FMVSS 302)
Glow Wire Flammability Index (GWFI)	650	°C	IEC 60695-2-12
GWFI - thickness tested (1)	3	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1

Other properties	Value	Unit	Test Standard
Density	1170	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	85	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.2	%	-
Melt temperature	230 - 250	°C	-
Mold temperature	70 - 90	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Special Characteristics

Heat stabilized or stable to heat