

Estadiene 0417 GF

ABS-GF17

Cossa Polimeri S.r.l.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	9	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Break	60	MPa	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	5000	MPa	ASTM D 790
Izod Impact notched, 1/8 in	70	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
Other properties			
Density	1150	kg/m ³	ASTM D 792

Characteristics**Features**

Thermal Stability

Regional Availability

Europe