

Polifil® GFABS-30

ABS-GF30

The Plastics Group of America

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	6.5	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	3.8	kg	-
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	6274	MPa	ASTM D 638
Tensile Strength	89.6	MPa	ASTM D 638
Elongation at Yield	2	%	ASTM D 638
Elongation at Break	2	%	ASTM D 638
Flexural Modulus	6412	MPa	ASTM D 790
Flexural Strength	116	MPa	ASTM D 790
Rockwell Hardness	R 118	-	ASTM D 785
Gardner Impact	0.452	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	53.4	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	107	°C	ASTM D 648
DTUL @ 264 psi	100	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.15	%	ASTM D 570
Density	1280	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Features

Low Odor

Applications

Automotive

Regional Availability

North America