

**4LAC 10H20800**

ABS

4Plas

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>2600</b>	MPa	ISO 527
Stress at break	<b>43</b>	MPa	ISO 527
Strain at break	<b>3</b>	%	ISO 527
Izod notched impact strength, +23°C	<b>15</b>	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Vicat softening temperature, B	<b>108</b>	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1040</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Regional Availability**

Europe