

4LAC 10H23100 A-M

ABS

4Plas

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	270	°C	-
Load	2.16	kg	-
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	2300	MPa	ISO 527
Stress at break	44	MPa	ISO 527
Strain at break	3	%	ISO 527
Izod notched impact strength, +23°C	40	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	104	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	118	°C	ISO 75-1/-2
Vicat softening temperature, B	124	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
Other properties			
Density	1180	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Flame retardant

Features

Fungus Resistance

Regional Availability

Europe