

4LAC 25H20800

ABS

4Plas

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2600	MPa	ISO 527
Stress at break	43	MPa	ISO 527
Strain at break	3	%	ISO 527
Izod notched impact strength, +23°C	15	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, B	108	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Europe