

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	230	°C	-
Load	3.8	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	40	MPa	ISO 527
Yield strain	2.5	%	ISO 527
Strain at break	6	%	ISO 527
Izod impact strength, +23°C	30	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	12	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Vicat softening temperature, B	99	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1050	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Delivery form

Black

### Certifications

Recycled Resin Content

### Regional Availability

Europe